


# MATERIAL TEST DATA

TRP COMPOUND REFERENCE  
N°: B106 (page 1 of 2)

Polymer Type: (SBR) Styrene Butadiene Rubber




## Description

A black Styrene butadiene Copolymer (SBR) material with good abrasion resistance. The material is formulated to give a smooth finish when ground, for use in fold roller applications for paper handling equipment, but it is also used for vibration

mounts and bridge bearings. Not suitable for use with mineral oil and petroleum based oils and fuels. **Service Temperatures  $-25^{\circ}\text{C}$  ( $-13^{\circ}\text{F}$ ) to  $+90^{\circ}$  ( $+194^{\circ}\text{F}$ ).**

TYPICAL PHYSICAL PROPERTIES	Property	Typical Values	Test Standard
	Colour	Black	
	Hardness ( $^{\circ}\text{IRHD}$ )	75	ISO 48
	Tensile Strength (MPa)	18.5	ISO 37
	Modulus @ 100% (MPa)	2.81	ISO 37
	Elongation @ Break (%)	414	ISO 37
	Tear Strength (N/mm)	64.7	ISO 34
	Specific Gravity ( $\text{g}/\text{cm}^3$ )	1.39	ISO 2781



H I G H P E R F O R M A N C E E L A S T O M E R S

# MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: B106 (page 2 of 2)

Polymer Type: (SBR) Styrene Butadiene Rubber

AIR-AGEING	Property (after 168 hours @ 100°C)	Typical Values	Test Standard
	Hardness Change (°IRHD)	-1	ISO 188
	Tensile Change (%)	-60	ISO 188
	Elongation Change (%)	-44.4	ISO 188
	Property (after 336 hours @ 100°C)	Typical Values	Test Standard
	Hardness Change (°IRHD)	+3	ISO 188
	Elongation Change (%)	-16.7	ISO 188

ABSORPTION TEST	Property (after 168 hours @ 100°C)	Typical Values	Test Standard
	IRM 901 OIL		
	Volume Change (%)	+20.13	ISO 1817
	Hardness Change (°IRHD)	-21	
	Distilled Water		
Volume Change (%)	+9.75	ISO 1817	
Hardness Change (°IRHD)	-4		

The properties given on this data sheet is derived from tests carried out by TRP Polymer Solutions Ltd. They should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

Data Sheet	Page	Issue Date	Issue No.	Issue By
MD233	2 OF 2	08.09.14	1	CEV

H I G H P E R F O R M A N C E E L A S T O M E R S