
MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: P161 (page 1 of 2)

Polymer Type: Polychloroprene (Neoprene™)

Description

This black Neoprene[™] can be used in a wide range of chemical applications, offering a degree of resistance to oils and solvents. It has good resistance to degradation from UV, Ozone and weather. This compound is formulated to meet the requirements of BS2752 C50.



Service Temperatures -30°C (-22°F) to +100°C (+212°F).

2

Ш

Σ

S


ш

ш

I

Neoprene™ is registered trade mark of a DuPont.

| | Property | Typical Values | Test Standard |
|-----------------------------|--------------------------|----------------|---------------|
| TYPICAL PHYSICAL PROPERTIES | Colour | Black | |
| | Hardness (°IRHD) | 54 | ISO 48 |
| | Tensile Strength (MPa) | 14.8 | ISO 37 |
| | Modulus @ 100% (MPa) | 3.28 | ISO 37 |
| | Elongation @ Break (%) | 421 | ISO 37 |
| | Tear Strength (N/mm) | 26.21 | ISO 34 |
| | Specific Gravity (g/cm³) | 1.38 | ISO 2781 |





MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: P161 (page 2 of 2)

Polymer Type: Polychloroprene (Neoprene™)

| | Property (after 168 hours @ 70°C) | Typical Values | Test Standard |
|------------|-----------------------------------|-----------------------|---------------|
| AIR-AGEING | Hardness Change (°IRHD) | +5 | ISO 188 |
| | Tensile Change (%) | -0.12 | ISO 188 |
| | Elongation Change (%) | -2.19 | ISO 188 |
| AG | | | |
| IR-, | Property (after 336 hours @ 70°C) | Typical Values | Test Standard |
| A | Hardness Change (°IRHD) | +7 | ISO 188 |
| | Tensile Change (%) | -2.44 | ISO 188 |
| | Elongation Change (%) | -6.14 | ISO 188 |

| | Property (after 168 hours @ 80°C) | Typical Values | Test Standard |
|-----------------|-----------------------------------|----------------|---------------|
| | IRM 901 OIL | | |
| | Volume Change (%) | +0.23 | ISO 1817 |
| EST | Hardness Change (°IRHD) | +4 | |
| ABSORPTION TEST | | | |
| Ö | IRM 903 OIL | | |
| 3PT | Volume Change (%) | +45.3 | ISO 1817 |
| SOI | Hardness Change (°IRHD) | -15 | |
| AB | | | |
| | DISTILLED WATER | | |
| | Volume Change (%) | +32.5 | ISO 1817 |
| | Hardness Change (°IRHD) | -10 | |

Ш

Ш

The properties given on this data sheet is derived from tests carried out by TRP Polymer Solutions Ltd. They should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

| Data Sheet | Page | Issue Date | Issue No. | Issue By |
|------------|--------|------------|-----------|----------|
| MD142 | 2 OF 2 | 22.07.11 | 1 | GV |

