MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: TRPlast® 260B Universal Black

Polymer Type: Perfluoroelastomer (FFKM)

Description

This black FFKM material is designed for sealing applications requiring best in class chemical resistance. It has excellent compression set properties and this grade is particularly suitable for prolonged use with strong acids.

Service Temperature: +260°C (+446°F) to −23°C (-9°F).



Along with all our TRPlast® range, this grade is suitable for use in a wide range of applications where other polymers are not suitable. Do not use any TRPlast® grade with molten alkali metals.

بِ	
5	S
Š	띮
Ŧ	R
_	PE
⋖	80
풆	<u></u>
⋝	

Property	Typical Values	Test Standard			
Colour	Black				
Hardness (IRHD)	77	ISO 48			
Tensile Strength (MPa)	23.3	ISO 37			
Modulus @ 100% (MPa)	16.4	ISO 37			
Elongation @ Break (%)	153	ISO 37			
Tear Strength (N/mm)	25.2	ISO 34			
TR10 (°C)	-8	ISO 2921			
Specific Gravity (g/cm³)	1.98	ISO 2781			
Compression Set Value in Air, 25% Strain, 24 HRS @ 204°C (%)	10.3	ISO 815			

ᆉ	S
2	A
E	IST
I	S

Chemical Group	Rating	Chemical Group	Rating
Aromatics/Aliphatic oils	1	Ethylene	1
Acids	1	Esters	1
Alkalis	1	Ketones	1
Alcohols	1	Propylene Oxide	1
Aldehydes	1	Steam/Hot Water	1
Amines	1	Strong Oxidisers	1
Ethers	1	Amines >70°C	2

- 1 Suitable, little or no effect.
- 2 Minor to moderate effect, not maximum resistance.
- 3 Moderate to severe effect may be useful in some limited applications.
- 4 Unsuitable and not recommended severe effect

More detailed information available on request

The service limit provided on this datasheet is stated as 15°C below the TR10 value. It is generally accepted within the industry that an elastomer will seal to 15°C below the TR10 figure in static conditions, providing that compression of the seal takes place at ambient conditions. TRP Polymer Solutions Ltd. Recommends that seals are evaluated in service before specification.

The properties given on this data sheet is derived from tests carried out by TRP Polymer Solutions Ltd. They should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

Data Sheet	Page	Issue Date	Issue No.	Issue By
MD334	1 OF 1	13.07.21	3	СС

