## MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: TRPlast® 260G Universal Green

Polymer Type: Perfluoroelastomer (FFKM)

## Description

This green FFKM material provides outstanding temperature resistance up to +260°C (+500°F) and has similar chemical resistance to that of PTFE but with elastomeric properties comparable to standard fluorocarbon rubbers. Along with all our TRPlast® range, this grade is suitable for use in a wide range of applications where other polymers are not suitable.



Do not use any TRPlast® grade with molten alkali metals.

Service Temperatures: +260°C (+500°F) to -22°C (-8°F).

are not suitable.		1200 0 (1300 1) 10 22	200 € (1300 1) (0 22 € ( 0 1).		
	Property	Typical Values	Test Standard		
	Colour	Green			
TYPICAL PHYSICAL PROPERTIES	Hardness (°IRHD)	72	ISO 48		
	Tensile Strength (MPa)	15.6	ISO 37		
	Modulus @ 100%	13.1	ISO 37		
	Elongation @ Break (%)	129	ISO 37		
	Tear Strength (N/mm)	15.9	ISO 34		
	TR10 (°C)	-7	ISO 2921		
	Specific Gravity (g/cm³)	2.54	ISO 2781		
	Compression Set Value in Air, 25% Strain, 24 hrs @ 204°C (%)	25.8	ISO 815		

ب	H
IICA	NY.
TEN T	SIST
Ü	Ä

Chemical Group	Rating	Chemical Group	Rating
Aromatics/Aliphatic oils	1	Ethylene	1
Acids	2	Esters	1
Alkalis	1	Ketones	1
Alcohols	1	Propylene Oxide	1
Aldehydes	1	Steam/Hot Water	1
Amines	1	Strong Oxidisers	1
Ethers	1	Amines >70°C	2

- 1 Suitable, little or no effect.
- 2 Minor to moderate effect, not maximum resistance.
- 3 Moderate to severe effect may be useful in some limited applications.
- 4 Unsuitable and not recommended severe effect

More detailed information available on request

The service limit provided on this datasheet is stated as 15°C below the TR10 value. It is generally accepted within the industry that an elastomer will seal to 15°C below the TR10 figure in static conditions, providing that compression of the seal takes place at ambient conditions. TRP Polymer Solutions Ltd. Recommends that seals are evaluated in service before specification.

The properties given on this data sheet is derived from tests carried out by TRP Polymer Solutions Ltd. They should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

Data Sheet	Page	Issue Date	Issue No.	Issue By
MD389	1 OF 1	13.07.21	3	СС

