

MATERIAL TEST DATA

TRP COMPOUND REFERENCE
Nº: TRPlast® 300AED High Temperature
Explosive Decompression Resistant

Polymer Type: Perfluoroelastomer (FFKM)



Description

This black rapid gas decompression resistant (RGD) material provides excellent temperature resistance up to +300°C (+572°F) and has similar chemical resistance to that of PTFE but with elastomeric properties comparable to standard fluorocarbon rubbers. Developed for high temperature water and steam applications.

Along with all our TRPlast® range, this grade is suitable for use in a wide range of applications where other polymers are not suitable. Do not use any TRPlast® grade with molten alkali metals. Service Temperatures +300°C (+572°F) to -18°C (+0°F)

TYPICAL PHYSICAL PROPERTIES	Property	Typical Values	Test Standard
	Colour	Black	
	Hardness (°IRHD)	92	ISO 48
	Tensile Strength (MPa)	21.8	ISO 37
	Elongation @ Break (%)	92	ISO 37
	Tear Strength (N/mm)	27.1	ISO 34
	TR10 (°C)	-3	ISO 2921
	Specific Gravity (g/cm³)	1.97	ISO 2781
	Compression Set Value in Air, 25% Strain, 24 hrs @ 204°C (%)	20.9	ISO 815

CHEMICAL RESISTANCE	Chemical Group	Rating	Chemical Group	Rating
	Aromatics/Aliphatic oils	1	Ethylene	1
	Acids	1	Esters	1
	Alkalis	1	Ketones	1
	Alcohols	1	Propylene Oxide	1
	Aldehydes	1	Steam/Hot Water	1
	Amines	1	Strong Oxidisers	1
	Ethers	1	Amines >70°C	2
	1 Suitable, little or no effect. 2 Minor to moderate effect, not maximum resistance. 3 Moderate to severe effect - may be useful in some limited applications. 4 Unsuitable and not recommended - severe effect More detailed information available on request			

The service limit provided on this datasheet is stated as 15°C below the TR10 limit. It is generally accepted within the industry that an elastomer will seal to 15°C below the TR10 figure in static conditions, providing that compression of the seal takes place at ambient conditions. TRP Polymer Solutions Ltd. Recommends that seals are evaluated in service before specification.

Data Sheet	Page	Issue Date	Issue No.	Issue By
MD101	1 of 1	14.07.21	3	CC