MATERIAL TEST DATA

TRP COMPOUND REFERENCE N°: TRPlast[®] LT-27 Intermediate low temperature

Polymer Type: Perfluoroelastomer (FFKM)

Description

This black intermediate low temperature material provides superior low temperature properties over standard FFKM grades whilst providing a cost effective alternative to traditional low temperature FFKM's. This material has similar chemical resistance to that of PTFE but with elastomeric properties comparable to standard fluorocarbon rubbers.



Along with all our TRPlast[®] range, this grade is suitable for use in a wide range of applications where other polymers are not suitable. Do not use any TRPlast[®] grade with molten alkali metals.

Service Temperatures: +230°C (+446°F) Max to -27°C (-17°F).

	Property	Typical Values	Test Standard
PROPERTIES	Colour	Black	
	Hardness (°IRHD)	77	ISO 48
	Tensile Strength (MPa)	17.1	ISO 37
	Modulus @ 100% (MPa)	8.68	ISO 37
	Elongation @ Break (%)	176	ISO 37
	Tear Strength (N/mm)	15.3	ISO 34
	Specific Gravity (g/cm ³)	1.99	ISO 2781
	Compression Set Value in Air, 25% Strain, 24 hrs @ 204°C (%)	14.5	ISO 815
	Low Temperature TR10 (°C)	-12	ISO 2921

Chemical Group	Rating	Chemical Group	Rating
Aromatics/Aliphatic oils	1	Ethylene	1
Acids	1	Esters	1
Alkalis	1	Ketones	1
Alcohols	1	Propylene Oxide	1
Aldehydes	1	Steam/Hot Water	1
Amines	1	Strong Oxidisers	1
Ethers	1	Amines >70°C	2

1 Suitable, little or no effect.

2 Minor to moderate effect, not maximum resistance.

3 Moderate to severe effect - may be useful in some limited applications.

4 Unsuitable and not recommended - severe effect

More detailed information available on request

The service limit provided on this datasheet is stated as 15°C below the TR10 value. It is generally accepted within the industry that an elastomer will seal to 15°C below the TR10 figure in static conditions, providing that compression of the seal takes place at ambient conditions. TRP Polymer Solutions Ltd. Recommends that seals are evaluated in service before specification.

The properties given on this data sheet is derived from tests carried out by TRP Polymer Solutions Ltd. They should not be regarded as specifications, but only as typical properties of the material described. It is intended for use by persons having technical skills and understanding of the seal and gasket design. Since the conditions of use are outside our control, nor have we designed the product shape, we can make no warranties, express or implied and assume no liability in connection with any use of this information.

Data Sheet	Page	Issue Date	Issue No.	Issue By
MD412	1 of 1	01.11.21	2	CC



RESISTANCE

CHEMICA

TRP Polymer Solutions Ltd. Netherwood Road, Rotherwas Industrial Estate, Hereford HR2 6JU Tel: +44 (0) 1432 268899 Fax: +44 (0) 1432 359594 Email: sales@trp.co.uk Web: www.trp.co.uk